

























MAGNET CATALOG



















Magfine Corporation

Japan +81 022 281 3956 Miyagi Sendai-shi Taihaku-ku Moniwa-aza-hitokitanishi 111-10 Japan 982-0251

Italia +39 0566 53094 Via del Fonditore, 806, 58022 Follonica (GR) Italia

Copyright © Magfine Corporation. Published 2020 March

IMG	CODE	MATERIAL	DIMENSIONS	FLUX DENSITY	ATTRACTIVE FORCE
	FD0029	Anisotropic Ferrite	Φ3mmX6mm	135.2mT	0.038kgf
	FD0007	Anisotropic Ferrite	Φ5mmX1.5mm	81.7mT	0.037kgf
	FD0011	Anisotropic Ferrite	Φ5mmX2mm	99.2mT	0.044kgf
	FD0025	Anisotropic Ferrite	Φ6mmX2mm	92.7mT	0.056kgf
	FD0030	Anisotropic Ferrite	Φ6mmX4mm	133.6mT	0.105kgf
	FD0013	Anisotropic Ferrite	Φ8mmX3mm	104.6mT	0.105kgf
	FD0032	Anisotropic Ferrite	Φ8mmX5mm	136.1mT	0.179kgf
	FD0015	Anisotropic Ferrite	Φ10mmX3mm	92.2mT	0.151kgf
	FD0016	Anisotropic Ferrite	Φ10mmX5mm	126.7mT	0.229kgf
	FD0033	Anisotropic Ferrite	Φ10mmX6mm	137.6mT	0.271kgf
	FD0027	Anisotropic Ferrite	Φ10mmX10mm	160.2mT	0.367kgf
	FD0035	Anisotropic Ferrite	Φ12mmX5mm	117.6mT	0.271kgf
	FD0036	Anisotropic Ferrite	Φ13mmX4mm	97.4mT	0.26kgf
	FD0037	Anisotropic Ferrite	Φ15mmX3mm	69.9mT	0.26kgf
	FD0005	Anisotropic Ferrite	Φ15mmX4mm	88.6mT	0.323kgf
	FD0006	Anisotropic Ferrite	Φ15mmX8mm	137.4mT	0.55kgf
	FD0006N	Anisotropic Ferrite	Φ15mmX8mm N Pole Marking	137.4mT	0.55kgf
	FD0023	Anisotropic Ferrite	Φ17mmX3mm	63.2mT	0.297kgf
	FD0002	Anisotropic Ferrite	Φ18mmX8.5mm	131.3mT	0.702kgf
	FD0008	Anisotropic Ferrite	Φ20mmX3mm	55.7mT	0.347kgf
	FD0018	Anisotropic Ferrite	Φ20mmX4mm	71.9mT	0.466kgf
	FD0010	Anisotropic Ferrite	Φ20mmX5mm	86.6mT	0.555kgf
	FD0039	Anisotropic Ferrite	Φ20mmX6mm	99.7mT	0.614kgf
	FD0022	Anisotropic Ferrite	Φ20mmX10mm	137mT	0.919kgf

IMG	CODE	MATERIAL	DIMENSIONS	FLUX DENSITY	ATTRACTIVE FORCE
	FD0040	Anisotropic Ferrite	Φ22mmX10mm	131.1mT	1kgf
	FD0001	Anisotropic Ferrite	Φ24mmX10mm	124.8mT	1.08kgf
	FD0003	Anisotropic Ferrite	Φ24.6mmX7mm	96.4mT	0.911kgf
	FD0021	Anisotropic Ferrite	Φ25mmX4mm	59.4mT	0.588kgf
	FD0041	Anisotropic Ferrite	Φ25mmX8mm	105.1mT	0.991kgf
	FD0004	Anisotropic Ferrite	Φ30mmX6.5mm	77.5mT	1.14kgf
	FD0043	Anisotropic Ferrite	Φ30mmX8mm	91.7mT	1.31kgf
	FD0020	Anisotropic Ferrite	Φ30mmX10mm	108.1mT	1.45kgf
	FD0044	Anisotropic Ferrite	Φ30mmX11mm	115.3mT	1.48kgf
	FD0045	Anisotropic Ferrite	Φ30mmX15mm	137.8mT	2.06kgf
	FD0046	Anisotropic Ferrite	Φ38mmX10mm	90.8mT	2.12kgf
	FD0048	Anisotropic Ferrite	Φ38mmX14mm	115.6mT	2.4kgf
	FD0050	Anisotropic Ferrite	Φ38mmX15mm	120.8mT	2.54kgf
	FD0014	Anisotropic Ferrite	Φ40mmX5mm	47.2mT	1.15kgf
	FD0047	Anisotropic Ferrite	Φ50mmX5mm	38.2mT	1.36kgf
	FD0049	Anisotropic Ferrite	Φ50mmX10mm	72.4mT	3.04kgf
	FD0024	Anisotropic Ferrite	Φ60mmX20mm	108.1mT	6.02kgf
	FD0051	Anisotropic Ferrite	Φ80mmX20mm	87.2mT	9.64kgf