

Specifications

Product Name	Neodymium $\Phi 5\text{mm} \times 6.5\text{mm}$				
Product Code	ND0411				
Content	Name	Symbol	SI	CGS	
Shape	Diameter	D	5 mm	0.5 cm	
	Height	H	6.5 mm	0.65 cm	
	Dimensional tolerance +/-	D H	0.1 mm 0.1 mm	0.01 cm 0.01 cm	
	Magnetization direction	M	Axial direction		
	Surface treatment	NiCuNi	12 μm	-	
Magnetic Properties	Surface flux density	B	454.5 mT	4545 G	
	Attractive and Adsorptive Force	F	0.939 kgf	939 gf	
	Operating Point Flux Density	Bd	985.3 mT	9853 G	
	Total Flux	ϕ_0	0.00001934 Wb	1934 Mx	
	Permeance Coefficient	Pc	4.94 Pc	-	
	Operating Temperature Limit	Tw	120 $^{\circ}\text{C}$	248 $^{\circ}\text{F}$	
Material Properties	Material Symbol	Neodymium	35		
	Residual Flux Density	Br	1170-1220 mT	11.7-12.2 kG	
	Coercive Force	Hcb	≥ 868 kA/m	≥ 10.9 kOe	
	Intrinsic coercive force	Hcj	≥ 955 kA/m	≥ 12 kOe	
	Maximum energy product	BH	263-287 kJ/m3	33-36 MGOe	
	Temperature coefficient	Br	-0.12 %/ $^{\circ}\text{C}$	31.78 %/ $^{\circ}\text{C}$	
		Hcj	-0.55 %/ $^{\circ}\text{C}$	31.01 %/ $^{\circ}\text{C}$	
	Heat resistance temperature	Tw	≤ 80 $^{\circ}\text{C}$	≤ 176 $^{\circ}\text{F}$	
	Curie temperature	Tc	310 $^{\circ}\text{C}$	590 $^{\circ}\text{F}$	
	Density	ρ	7.5 kg/m3	-	
Remarks	Weight	Net	0.000957 kg	0.957 g	
	REACH RoHS Directive				

All magnetic property values are for reference only. Please use them only as reference values when referring to actual magnetic application products or for research and development. We are not responsible for any liability resulting from the use of reference values. The contents of this document are subject to change without notice due to improvements or other reasons.